

Five Minute Epoxy Mortar

EPAR 705/EX 5 Minute Epoxy

TECHNICAL DATA

1.0 DESCRIPTION

Two part, low-slump epoxy mortars with 5-minute gel times formulated to give a strong bond to dry or damp concrete, steel, glass, aluminium etc. Both EPAR 705 & EPAR EX 5 minute epoxies are non-shrink and have excellent chemical resistance.

2.0 PROPERTIES

2.1. Viscosity	Low Slump
2.2. Mix Ratio	1:1 by weight or volume
2.3. Pot Life	Less than 5 minutes at 25°C
2.4. Minimum Application Temp.	-9°C
2.5. Shelf Life	1 year in original unopened containers
2.6. Cured Properties	(at 20°C – full cure after 7 days)
2.6.1. Colour	Grey, blends with most normal concrete.
2.6.2. Specific Gravity	1.78

3.0 USES

EPAR 705/EX 5-minute systems are used where a 5-minute gel time and over 90% cure in 1 – 2 hours is required. Typically they are used in applications where short curing times are essential. Also, 5-minute mortars may be used where cold and damp conditions are experienced.

Common uses for a 5-minute epoxy mortar include the following:

- 3.1 Bedding and jointing of precast concrete units.
- 3.2 Repair of damaged or spalled concrete and protection of reinforcing.
- 3.3 Levelling and patching of concrete floors under heavy load or impact.
- 3.4 Grouting of starter bars and bolts particularly horizontal or overhead.
- 3.5 Fabrication of concrete pipe intersections and general drainage work, including underground work.
- 3.6 Raised pavement markers (road markers).

4.0 APPLICATION

- 4.1. **SURFACE PREPARATION.** Thoroughly clean the jointing surfaces of all extraneous matter, especially oil and grease. Laitence should be removed from concrete surfaces mechanically or by acid etching. For best results, steel surfaces should be prepared by sand blasting or grinding. All surfaces should be dry.



Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: www.fbsltd.co.nz Email: info@fbsltd.co.nz

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.



Registered
No. 1210
FBS 0702

EPAR 705/EX 5 Minute Epoxy

TECHNICAL DATA Continued

- 4.2. **MIXING PROPORTIONS** - 1: 1 by volume or weight. Mix the two parts THOROUGHLY by machine, spatula, or by hand until a uniform grey colour is obtained. For prolonged hand mixing, the use of rubber gloves and a barrier cream is recommended. Thoroughly wet hands in water to prevent sticking of EPAR. Shake off excess. Avoid mixing water with EPAR as this may interfere with the final set and hardness.
- Avoid mixing large amounts of EPAR 5-minute mortar that can not be used within the pot life of 5 minutes at 25°C.
- 4.3. In cold weather the resin and hardener may be softened by placing the containers in hot water.
- 4.4. **APPLICATION.** EPAR 5-minute mortars should be worked well into the surface to be filled or bonded. Initially a thin smear should be applied to ensure the surface is properly 'wet' with epoxy. After applying this initial layer more EPAR may be applied to the desired thickness. Both surfaces should be coated with EPAR before being joined. A smooth surface can be obtained by wiping with a wet cloth or trowel.
- If being placed under water, avoid involving water into the mixed EPAR. Use minimum amount of handling when placing and finishing.
- 4.5. **CLEAN UP.** Hands and equipment should be washed with soap and water before curing is advanced.


5.0 PACKAGING

900 gm pack (2 x 450 gm) - approx. volume 0.5 litres

1.8 kg pack (2 x 900 gm) - approx. volume 1 litre (EPAR 705 only)

3.6 kg pack (2 x 1.8 kg) - approx. volume 2 litres

16 kg pack (2 x 8 kg) - approx. volume 9 litres (EPAR 705 only)



Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: www.fbsltd.co.nz Email: info@fbsltd.co.nz

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.



FBS 0702