

SOLVENT-BASED ACRYLIC CONCRETE SEALER

HARDCOAT

TECHNICAL DATA

1.0 DESCRIPTION

HARDCOAT is a solvent-based acrylic resin solution for use on concrete (normal and coloured), masonry & slate to seal the surface. It is used to put a clear glaze on ground/polished concrete floors, exposed aggregate, concrete roof tiles, imprinted (stamped) concrete drives, paths, etc. It helps maintain the surface clean and prevent pigment leach-out. HARDCOAT has good UV and weather resistance.

2.0 PHYSICAL PROPERTIES

2.1. Colour	Clear. Dries to a satin finish.
2.2. Specific Gravity	0.90
2.3. Flash Point	24°C. Flammable. Avoid all sources of ignition.
2.4. Viscosity	Low
2.5. Min. Application Temp.	5°C substrate temperature.
2.6. Toxicity	Poisonous. Contains aromatic hydrocarbon mixture including Xylene. Non-toxic when dry. MSDS available on request.
2.7. D.G. Classification	3.1c
2.8. Shelf Life	Over 1 yr. in sealed container.
2.9. Coverage	Broomed Surface: 7m ² per litre per coat. Trowelled Surface: 12m ² per litre per coat. (Coverage is approximate depending on surface porosity)

3.0 USES

HARDCOAT is used to put a clear glaze on concrete and masonry surfaces such as footpaths, driveways, lock-ups, garages, industrial floors, concrete roof tiles and other concrete articles, including exposed aggregate panels, etc. Also for use on stonework to 'lift' the colour & slate sealing but avoid excess application.

HARDCOAT provides a weatherproof, stain resistant and dustproof sealer. It may be used to seal dusting and porous surfaces to help against further degradation.

HARDCOAT is formulated to enhance the beauty of concrete surfaces.

HARDCOAT is resistant to rain, sun, water and grease offering excellent durability with good colour retention and clarity. HARDCOAT is non-yellowing.

4.0 BENEFITS

HARDCOAT offers the following benefits and advantages:

- Touch dry in 30 minutes. Can be opened to foot traffic in one to 2 hours (external application with good drying conditions).
- Resists weather, providing a clear, tough, easy to clean film.
- Contains a UV stabiliser to prevent yellowing in exterior applications.
- Provides a dustproof surface.
- Dries to a low-medium sheen. Additional coats can be applied to increase sheen.
- May be used on internal concrete surfaces (good ventilation required).



Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: www.fbsltd.co.nz

Email: info@fbsltd.co.nz

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.



HARDCOAT

TECHNICAL DATA Continued

5.0 APPLICATION

- 5.1. The surface to be treated must be clean and dry prior to application (i.e., uncoated and unsoiled). Stains, oil, grease and any other surface contaminants must be removed. Old stains not removed from the surface will be visible after the film dries.
- 5.2. New concrete should be allowed to hydrate and dry for at least 14 days, preferably 28 days. Film-forming curing compounds, other than CS-309 Acrylic Curing Compound, must be removed before application of HARDCOAT.
- 5.3. Very dense new concrete surfaces should be 'deglazed' by washing with a dilute solution of Hydrochloric or MISTIC Acid, washed and allowed to dry.
- 5.4. The surface should be as dry as possible to permit maximum penetration of HARDCOAT.
- 5.5. Apply 1 - 2 coats of HARDCOAT as supplied, depending upon surface absorbency and sheen requirements. Two thin coats will give superior performance to one thick coat. Additional thin coats may be applied depending on requirements. Use a roller, brush or airless sprayer to apply. The first coat should be completely dry before application of the second coat. Usually 12 hours is sufficient under good drying conditions.
- 5.6. Allow at least 1 - 2 hours before opening treated areas to foot traffic, and preferably overnight before opening to wheeled traffic.

Clean up with HARDCOAT Solvent or Xylene.

6.0 PRECAUTIONS

- 6.1. Avoid excess coating as the surface may become glossy, and therefore slippery in the wet. For better slip resistance, it is possible to "sand" the penultimate coat of HARDCOAT using dry, white, silica sand or incorporate slip-reducing additives into the HARDCOAT during application (stir well regularly).
- 6.2. Being only a thin coating, HARDCOAT will wear, but can easily be overcoated, as it is resoluble.
- 6.3. Do not apply HARDCOAT if the temperature of the substrate is below 5°C. Check drying time if applied internally and allow extra time before opening floor to traffic. Ensure good through ventilation (mechanical if required) during and after application until completely dried.
- 6.4. Due to the surface variations inherent to coloured concrete surfaces, slate and masonry products, test HARDCOAT before applying. Determine required sheen level by applying one, two or more coats before proceeding with complete application. Additives and fillers used in concrete may result in random variations in porosity, thereby affecting coverage and sheen levels. Additional coats may be required to provide proper surface treatment. Note that being a clear acrylic, HARDCOAT will darken surfaces to which it is applied, and the effect will be greater with additional coats.
- 6.5. Soft rubber tyres, such as forklift tyres, may mark HARDCOAT if allowed to skid on the treated surface.
- 6.6. HARDCOAT contains a mixture of aromatic hydrocarbon solvents and must be treated with care. Use in well ventilated areas. Avoid excessive inhalation of fumes. Do not smoke. Keep containers sealed and away from ignition sources and heat. Wear protective clothing and avoid skin contact. If applied internally, the area must be well ventilated and if necessary, wear self-contained breathing apparatus.

Refer to Material Safety Data Sheet for handling and first aid information.

7.0 PACKAGING

4, 20 and 200 litres.



Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: www.fbsltd.co.nz

Email: info@fbsltd.co.nz

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.

