allco WATERPROOFING SOLUTIONS

PRIMER SELF ADHESIVE MEMBRANE



Allco Self-Adhesive Membrane Primer is used to prepare suitable substrates before the installation of self-adhesive membranes and vapour barriers. The solvent-based formulation combines synthetic rubber and resins to support a strong bond between the substrate and membrane system.

It is suitable for a wide range of substrate types where improved adhesion is required before applying self-adhesive waterproofing or vapour control membranes.

DESIGNED FOR:

- Metallic surfaces
- Bituminous materials
- Wood-based panels
- Insulation boards

ADVANTAGES

- **Immediate access:** Flashes off in just 1—2 minutes, creating a dry surface that can be walked on safely without transfer to footwear or tools.
- **Non-MECL formulation:** Free from methylene chloride for a safer working environment.
- **Controlled application:** Adjustable spray system for precision and reduced waste.

TECHNICAL DATA

SHELF LIFE	36 Months
APPEARANCE	Black
TEMPERATURE RESISTANCE	-30°C - 90°C
SOLVENT SYSTEM	Non-Chlorinated
COVERAGE (BONDED AREA)	220m²
SOLIDS	35%
STORAGE	5°C - 25°C

DIRECTIONS FOR USE

- This product is designed to be applied to the roof deck. For best results, the temperature of the adhesive and the surfaces being bonded should be between 60°F - 80°F (16°C - 27°C).
- Use with adequate ventilation. When possible we recommend shaking the canister well before using.
- Attach and secure hose tightly onto the spray gun with required tip. Attach the other end of the hose onto the canister. Make sure the hosevalve connections are securely tight. Open the valve on the canister slowly and fully, check for leaks during this process. Unlock the trigger on the spray gun to start spraying.
- Prior to use, check compatibility by spraying a small test patch of the primer on the substrate. This product may degrade some substrates.

1. Make sure that surfaces are clean, dry and free from dirt, dust, oil, loose paint, wax or grease, etc.
2. Spray about 10-20 cm (4" — 8") away at a 90 degree angle to the surface, with 50% overlaps applying a uniform, even coat of adhesive to obtain 80% to 100% coverage of the surface. If necessary, spray another coat of primer in areas that appear to need more primer.
3. Allow 2 minutes for the primer to tack off until no primer transfers to the knuckle when touched.
4. Adhere surfaces and press together with adequate pressure. A roller is recommended to apply a uniform pressure to achieve maximum strength. Allow 24 hours for the adhesive to fully cure.
5. If the spray tip clogs, unscrew the spray tip from the gun and clean with solvent such as lacquer thinner or acetone. Do not use a pin on the spray tip.

CANISTER STORAGE & CHANGE OVER

Turn valve on canister into the off position, spray out remaining adhesive left in the hose, disconnect the spray hose and gun from the canister. Reconnect the spray hose to a canister of cleaning solvent (sold separately) and spray out until liquid is clear which indicates that the hose and gun is clean. If you choose to leave the hose and spray gun on the canister, leave the valve on the canister open. Do not disconnect the hose/gun from the canister. Close and lock the spray gun.

HANDLING & STORAGE

- Consult Material Safety Data Sheet prior to use.
- DO NOT store at temperatures over 50°C.
- Avoid exposure to direct sunlight.
- DO NOT store directly on concrete floor.
- For optimum performance, store at 18°C during use, but must always be above 10°C.
- When connected, keep valve open and hose pressurised at all times.
- DO NOT close valve until ready to connect to new cylinder.
- Release pressure in hose before disconnection.
- Always test product to determine suitability for your particular application prior to use in production.

HEALTH & SAFETY

Before handling or opening this product, obtain and read the Safety Data Sheet (SDS) available at www.sabreadhesives.com and ensure all safety precautions are followed.

FIRST AID

If poisoning occurs, contact a Doctor or Poisons Information Centre (Phone Australia 131 126; New Zealand 0800 764 766) and have the SDS and product label at hand.

STORAGE & SHELF LIFE

Do not store at temperatures over 50°C.
Avoid exposure to direct sunlight.
Avoid storing on cold concrete floors.
Shelf life 36 months from date of manufacture.

PACKAGING & COLOUR

Available colours: Black
Packaging size: Canister 22L

IMPORTANT NOTICE
Allco Waterproofing NZ makes no warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. User is responsible for determining whether the product is fit for a particular purpose and suitable for user's method of application. Due to the fact that specific substrates, such as: plastics, polycarbonates, etc, may differ from manufacturer to manufacturer we recommend preliminary compatibility tests. Please remember that many factors can affect the use and performance in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a product. Given the variety of factors that can affect the use of our products some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

LIMITATION OF REMEDIES AND LIABILITY
If the product is proved to be defective, the sole remedy shall be to refund the purchase price or to repair or replace the defective product. Sabre shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.