



TPO MEMBRANE ADHESIVE

Allco TPO Spray Membrane Adhesive is a professional-grade spray-applied bonding adhesive developed for use with TPO and smooth-back EPDM roofing membranes. Supplied in a convenient canister system, it delivers strong, reliable adhesion across a range of common roofing substrates, including concrete, plywood, metal decking, and paper-faced insulation boards.

Engineered for demanding roofing environments, Allco TPO Spray Membrane Adhesive performs well in a wide range of temperature conditions and allows the spray output to be adjusted to suit the application. This makes it suitable for precise detailing around edges, penetrations, and transitions, as well as rapid coverage across larger roof areas.

BENEFITS

- High build formulation
- Fast tack off
- High coverage
- Low VOC emissions
- Highly adjustable spray pattern



PREPARATION

- This product is designed to be applied to two surfaces to be bonded together. For best results, the temperature of the adhesive and the surfaces being bonded should be between 60°F - 80°F (16°C - 27°C).
- Use with adequate ventilation. When possible we recommend shaking the canister well before using.
- Attach and secure hose tightly onto the spray gun with required tip. Attach the other end of the hose onto the canister. Make sure the hose-valve connections are securely tight. Open the valve on the canister slowly and fully, check for leaks during this process. Unlock the trigger on the spray gun to start spraying.

- Prior to use, check compatibility by spraying a small test patch of the adhesive on the substrate. This product may degrade some substrates.
1. Make sure that surfaces are clean, dry and free from dirt, dust, oil, loose paint, wax or grease, etc.
 2. Spray about 10-20 cm (4" — 8") away at a 90 degree angle to the surface, applying a uniform, even coat of adhesive to obtain 80% to 100% coverage of the surface. If necessary, spray another coat of adhesive in areas that appear to need more adhesive.
 3. Spray both surfaces to be bonded, one surface vertically and the other surface horizontally.
 4. Allow 2 - 3 minutes for the adhesive to tack off until no adhesive transfers to the knuckle when touched.
 5. Adhere surfaces and press together with adequate pressure. A roller is recommended to apply a uniform pressure to achieve maximum strength. Allow 24 hours for the adhesive to fully cure.
 6. If the spray tip clogs, unscrew the spray tip from the gun and clean with solvent such as lacquer thinner or acetone. Do not use a pin on the spray tip orifice.

HANDLING & STORAGE

- Consult Material Safety Data Sheet prior to use.
- DO NOT store at temperatures over 50°C.
- Avoid exposure to direct sunlight.
- DO NOT store directly on concrete floor.
- For optimum performance, store at 18°C during use, but must always be above 10°C.
- When connected, keep valve open and hose pressurised at all times.
- DO NOT close valve until ready to connect to new cylinder.
- Release pressure in hose before disconnection.
- Always test product to determine suitability for your particular application prior to use in production.

CANISTER STORAGE & CHANGE OVER

Turn valve on canister into the off position, spray out remaining adhesive left in the hose, disconnect the spray hose and gun from the canister. Reconnect the spray hose to a canister of cleaning solvent (sold separately) and spray out until liquid is clear which indicates that the hose and gun is clean. If you choose to leave the hose and spray gun on the canister, leave the valve on the canister open. Do not disconnect the hose/gun from the canister. Close and lock the spray gun.

TECHNICAL DATA

SHELF LIFE	2 years
APPEARANCE	Red
TEMPERATURE RESISTANCE	-30°C to 100°C
SOLVENT SYSTEM	Flammable solvent system
COVERAGE (Double Sided)	90 m ²
SOLIDS	40 (+/- 2) %
STORAGE	Below 50°C

APPLICATION TOOLS

HOSE	Standard - 4 meter	
	Long - 8 meter	
GUN	Standard Spray Gun	
	Spray Gun & Wand	
SPRAY TIP	9501	

PACKAGING & COLOUR

Available colours: Red Packaging

Size: Canister 22L

Allco_TPO_Spray_Membrane_Adhesive_TDS_2607

IMPORTANT NOTICE

Allco Waterproofing NZ makes no warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. User is responsible for determining whether the product is fit for a particular purpose and suitable for user's method of application. Due to the fact that specific substrates, such as: plastics, polycarbonates, etc., may differ from manufacturer to manufacturer we recommend preliminary compatibility tests. Please remember that many factors can affect the use and performance in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a product. Given the variety of factors that can affect the use of our products some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

LIMITATION OF REMEDIES AND LIABILITY

If the product is proved to be defective, the sole remedy shall be to refund the purchase price or to repair or replace the defective product. Sabre shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.